

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
19 July 2001 (19.07.2001)

PCT

(10) International Publication Number
WO 01/51419 A1

- (51) International Patent Classification⁷: C01F 7/14, C08K 3/22
- (21) International Application Number: PCT/EP01/00182
- (22) International Filing Date: 10 January 2001 (10.01.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
00100429.0 10 January 2000 (10.01.2000) EP
- (71) Applicant (*for all designated States except US*): ALUSU-
ISSE MARTINSWERK GMBH [DE/DE]; Kölner
Strasse 110, 50127 Bergheim (DE).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): BROWN, Neil
[GB/DE]; Buchenweg 1, 50126 Bergheim (DE). PÜTZ,
Norbert [DE/DE]; Memeler Strasse 1, 50129 Bergheim
(DE).
- (74) Agent: RIEGLER, Norbert, Hermann; Lonza AG, P.O.
Box, CH-4002 Basel (CH).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- with international search report
 - before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments
- For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*



WO 01/51419 A1

(54) Title: PROCESS FOR THE PRODUCTION OF ALUMINIUM HYDROXIDE OF IMPROVED THERMAL STABILITY

(57) Abstract: Aluminium hydroxide of improved thermal stability is produced by spray-drying of an aqueous slurry of aluminium hydroxide at 400 to 600 °C drying gas temperature. The resulting aluminium hydroxide is suitable as a flame retardant filler in polymeric systems with high processing temperatures. It has a low specific surface area and good rheological properties.

Process for the Production of Aluminium Hydroxide of Improved Thermal Stability

The invention relates to a process for the production of an aluminium hydroxide of improved thermal stability which can be incorporated in plastic composite materials whose processing temperatures exceed 200 °C.

Aluminium hydroxide ($\text{Al}(\text{OH})_3$) is widely used as a flame retardant in polymeric systems. On heating to above a temperature of ca. 200 °C, the aluminium hydroxide begins to decompose to aluminium oxide and water. This reaction is endothermic, thus absorbing heat from the of the polymer. The amount of water released corresponds to 34.6 wt.% of the aluminium hydroxide. Both these factors act to suppress a burning process and reduce the formation of combustible gases by keeping the temperature down.

To be useful as a flame retardant, the aluminium hydroxide must remain stable during processing of the polymer. This renders it unsuitable for polymers which are processed above 200 °C.

Prior art indicates that one way around this limitation is to preheat the aluminium hydroxide to eliminate a part of the water which is released at elevated temperatures.

However, there are inherent disadvantages in this approach:

- The amount of water (vapour) available for the flame retardant action is reduced.
- A portion of the aluminium (tri)hydroxide on heating above 200 °C converts to aluminium oxide hydroxide (AlOOH , "alumina monohydrate") which contains only one third of the amount of water and which is thermally stable until ca. 520 °C, i. e., until a temperature well above the useful range for effective flame retardancy of plastic materials.
- Partial elimination of water as a means of stabilizing against subsequent early release of water vapour at elevated temperatures is accompanied by an increase in specific surface area of the aluminium hydroxide. This increased surface is in the form of fine porosity which imparts hygroscopic properties to the surface of the thermally stabilized crystals. Increased specific surface area is further accompanied by higher oil absorption and higher viscosity in synthetic resins.

The problem to be solved by the present invention was to provide a simple and economic process for the production of aluminium hydroxides of improved thermal stability, high water content and low specific surface area.

5 According to the invention, this problem has been solved by the process of claim 1.

It has been found that aluminium trihydroxide can be partially dehydrated at elevated temperatures without a concomitant increase in the specific surface area and with little or no creation of aluminium oxide hydroxide, provided that the residence time at the
10 dehydration temperature is sufficiently short. According to the present invention, this is accomplished by spray drying of an aqueous slurry of ordinary aluminium hydroxide at a drying gas temperature (at the inlet) of 400 to 600 °C.

Preferably, the drying gas temperature is 450 to 550 °C.

15

The exit gas temperature from the spray-dryer is preferably 200 to 300 °C.

The residence time of the aluminium hydroxide in the spray-dryer is preferably 0.5 to 10 s, more preferably 1 to 5 s.

20

Preferably, the average particle size of the starting aluminium hydroxide is 2 µm or less. Advantageously, coarse particles (e. g. >10 µm) are removed before spray drying. The aluminium hydroxide slurry used as starting material may be produced by crystallization from the sodium aluminate liquor of the Bayer process, filtering and thoroughly washing
25 with hot water, and re-slurrying in an amount of water sufficient to obtain a slurry suitable for feeding to a spray-dryer. Typically, the solids content of the slurry is 40 to 60 wt.%.

The process of the present invention achieves the goal of improved thermal stability with no significant increase in the specific surface area of the aluminium hydroxide, as
30 compared to the starting material, and without substantial decrease of the loss on ignition (LOI) values. Moreover, X-ray diffraction diagrams reveal the formation of trace quantities of aluminium oxide hydroxide (boehmite, AlOOH) only, hence indicating a maximum retention of the effective fire retardant aluminium trihydroxide.

The product of the present invention is of industrial importance especially in the application area of environment friendly printed circuit boards, where aluminium hydroxide can now be used to achieve the UL-94 V0 fire rating without the problems associated with the hygroscopic nature of the aluminium trihydroxide of the prior art, without raised viscosity levels and reduction in fire retardant effectiveness due to the presence of boehmite.

The following non-limiting examples illustrate the process of the present invention. The starting material in each example was aluminium hydroxide from different batches of the type Martinal® OL-104 (manufacturer: Alusuisse Martinswerk GmbH, Bergheim, Germany).

Comparative Example 1

Samples of aluminium hydroxide Martinal® OL-104 (Alusuisse Martinswerk GmbH, Bergheim, Germany) having a specific surface area of 3.75 m²/g were heated in an oven at various temperatures for different periods of time. The sample size was 100 g in each case. After the thermal treatment, the loss-on-ignition (LOI) and the specific surface area of each sample were measured and X-ray diffraction diagrams were recorded. The results obtained are given in Table 1.

Table 1

Temperature [°C]	Time [h]	LOI [wt.%]	Specific Surface [m ² /g]
180	1	34.4	3.85
180	2	34.1	3.92
180	4	33.6	4.10
200	1	33.5	4.47
200	2	33.1	5.30
220	1	32.7	6.76
220	2	30.7	34.2

The data indicate that the low temperature – extended time combination leads to increased specific surface area as loss-on-ignition decreases.

In all cases, some aluminium oxide hydroxide was formed as evidenced from X-ray diffraction.

5 Comparative Example 2

Untreated Martinal[®] OL-104 and the aluminium hydroxide obtained in Example 1 by the 200 °C/1 h treatment were dispersed in unsaturated polyester resin Synolite[®] 0020-N-2 (DSM BASF Structural Resins) using a filling level of 150 phr (parts per hundred resin).

- 10 Comparative viscosity measurements were made at 23 °C using a Brookfield HBT viscosimeter with Spindle 3 at 10 rpm. The results are given in Table 2.

Table 2

Aluminium Hydroxide	Viscosity [Pa·s]
Martinal [®] OL-104 (untreated)	150
Martinal [®] OL-104 (200 °C/1 h)	176

- 15 The results show that the heat treatment increased the viscosity of the resin/aluminium hydroxide mix by almost 20%.

Example 1

20

Approx. 5 kg of an aqueous slurry of Martinal[®] OL-104 (53 wt.% solids) were spray-dried in an Niro (Niro A/S, Soeborg, Denmark) spray-dryer (type "Production Minor") at a slurry feed rate of ca. 5 kg/h and an air flow of 300 kg/h. The inlet gas temperature was 480 °C and the exit temperature ca. 200 °C with a solids retention time of ca. 3 seconds.

- 25 Approximately 2.5 kg of product were recovered from the dryer. The product had a specific surface area of 4.3 m²/g and loss on ignition of 33.2 wt.% (starting material: 4.5 m²/g and 34.6 wt.%, respectively), i. e., the specific surface area was within the experimental error of the method unchanged.

- The rheological properties of the product were determined as described in Comparative
30 Example 2. The results are given in Table 3.

Table 3

Aluminium Hydroxide	Viscosity [Pa·s]
Martinal [®] OL-104 (untreated)	165
Martinal [®] OL-104 (treated)	160

The results show that the spray drying had no significant effect on the rheological properties of the product.

5

Example 2

Essentially the same procedure was adopted as in Example 1 except that the production was scaled up to the industrial level. This time a Niro dryer (type SD-0080-CN/CR) with a throughput of 150 to 450 kg per hour was used with an air flow of ca. 1000 kg/h. The starting material Martinal[®] OL-104 (specific surface area 4.6 m²/g) was slurried in water to give ca. 50 wt.% solids. The inlet temperature of the air to the dryer could be varied between 400 and 580 °C. The exit temperature varied between 200 and 300 °C. Total retention time in the reactor was 2–10 s. The dried product was bagged in plastic-lined paper bags.

The characteristics of the product were as follows:

Loss on Ignition (wt.%)	32.5
Specific Surface Area (m ² /g)	4.8
Oil Absorption (ml/100 g)	28
Viscosity in Synthetic Resin (Pa·s)	160

Claims

1. A process for the production of aluminium hydroxide of improved thermal stability,
comprising spray-drying of an aqueous slurry of aluminium hydroxide at a drying gas
5 temperature of 400 to 600 °C.
2. The process of claim 1, wherein the drying gas temperature is 450 to 550 °C.
3. The process of claim 1 or 2, wherein the exit gas temperature from the spray-dryer is
10 200 to 300 °C.
4. The process of any one of claims 1 to 3, wherein the residence time in the spray-dryer
is 0.5 to 10 s, preferably 1 to 5 s.
- 15 5. The process of any one of claims 1 to 4, wherein the average particle size of the
starting aluminium hydroxide is 2 µm or less.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 01/00182

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C01F7/14 C08K3/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C01F C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 807 603 A (SUMITOMO CHEMICAL CO) 19 November 1997 (1997-11-19) claims 4,5; example 1 ---	1-5
A	EP 0 277 730 A (SUMITOMO CHEMICAL CO) 10 August 1988 (1988-08-10) example 1 ---	1-5
A	US 5 378 753 A (BROWN STEPHEN C) 3 January 1995 (1995-01-03) example 1 ---	1-5
A	PATENT ABSTRACTS OF JAPAN vol. 011, no. 290 (C-447), 18 September 1987 (1987-09-18) & JP 62 083316 A (MITSUBISHI HEAVY IND LTD), 16 April 1987 (1987-04-16) abstract --- -/--	1-5

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *A* document member of the same patent family

Date of the actual completion of the international search

8 May 2001

Date of mailing of the international search report

15/05/2001

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Lehnert, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 01/00182

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0 143 576 A (WARNER LAMBERT CO) 5 June 1985 (1985-06-05) example 1 -----</p>	1-5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/00182

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0807603	A	19-11-1997	CA 2205518 A	16-11-1997
			JP 10059713 A	03-03-1998
			US 6130283 A	10-10-2000
EP 0277730	A	10-08-1988	DE 3870637 A	11-06-1992
			JP 2638873 B	06-08-1997
			JP 63303809 A	12-12-1988
			US 5302368 A	12-04-1994
US 5378753	A	03-01-1995	AT 65769 T	15-08-1991
			AU 589534 B	12-10-1989
			AU 7563587 A	21-01-1988
			BR 8703695 A	29-03-1988
			CA 1331504 A	23-08-1994
			DE 3771796 A	05-09-1991
			DK 371787 A	17-01-1988
			EP 0253635 A	20-01-1988
			FI 873096 A, B,	17-01-1988
			IN 169936 A	11-01-1992
			JP 63055113 A	09-03-1988
			NO 174619 B	28-02-1994
			US 4989794 A	05-02-1991
			US 5306480 A	26-04-1994
			US 5083712 A	28-01-1992
			ZA 8705122 A	30-03-1988
JP 62083316	A	16-04-1987	NONE	
EP 0143576	A	05-06-1985	CA 1201383 A	04-03-1986
			AU 3548484 A	30-05-1985
			JP 60123421 A	02-07-1985
			ZA 8408972 A	30-10-1985